

BATCH REPORT OF HARDNESS & DIMENSION TEST


Area : Compression

REPRINT


Product Name	KROCIN TABLET1		
Batch No.	BT-Summary Comp	Department	QC
BFG Code No.	KROCIN TABLET1	Stage	NA

Standard Limits					
Hardness(N)		Thickness (mm)		Length (mm)	
Lower =	50	Lower =	4.50	Lower =	9.50
Standard =	75	Standard =	5.00	Standard =	10.00
Upper =	100	Upper =	5.50	Upper =	10.50

Batch Summary			
Parameter	Minimum	Maximum	Average
Hardness(N)	50	100	75.4
Thickness(mm)	4.55	5.23	4.98
Length (mm)	9.58	10.23	9.98



Standard Upper Lower Min Max




Standard Upper Lower Min Max

BATCH REPORT OF HARDNESS & DIMENSION TEST

Area : Compression

REPRINT



Detailed Report

Test No.	Date	Time	Hardness Tester Code No.	Side	Hardness (N)		Thickness (mm)		Length (mm)		Test result	Performed by
					Min	Max	Min	Max	Min	Max		
1	13.11.2024	16:06:30	HRD_23	NA	50	99	4.55	4.99	9.58	9.99	Complies	Dipti
2	13.11.2024	16:20:03	HRD_23	NA	50	78	4.99	5.15	9.65	10.15	Complies	Dipti
3	13.11.2024	16:21:35	HRD_23	NA	78	90	5.11	5.55	10.11	10.99	Not Complies	Dipti
4	13.11.2024	16:22:24	HRD_23	NA	80	120	5.00	5.55	10.00	10.99	Not Complies	Dipti
5	13.11.2024	16:38:08	HRD_23	NA	80	100	5.00	5.23	10.00	10.23	Complies	Dipti
6	13.11.2024	16:47:48	HRD_23	NA	60	80	4.95	5.11	9.96	10.13	Complies	Dipti